










Auswahlkriterien in Elastomeren

	 Sillitin V 85	 Sillitin V 88	 Sillitin N 75	 Sillitin N 85	 Sillitin N 87	 Sillitin Z 86	 Sillitin Z 89	 Silfit Z 91	 Sillikolloid P 87
Farbneutralität	••	•••••	•	••	•••	••	••••	•••••	••
Extrusion	Profilausformung	•	•	•••	••	•••	•••	•••○	••••
	Standfestigkeit	•	•	•••	••	•••	•••	•••	••••
	Mattierungswirkung	••••	••••	•••	•••	••	••	••	•
Viskosität	•	•	•••	••	••	•••	•••	••○	••••
Zugfestigkeit	•	•	•••	••	••	•••	•••	•••	••••
Weiterreißwiderstand	•	•	•••	••	••	•••	•••	•••	••••
Druckverformungsrest	•	•	•••	••	••	•••	•••	•○	••••
Elastizität	••••	••••	•••	•••	•••	••	••	••	•
Abriebverlust	••••	••••	••	•••	•••	••	••	••	•

Eigenschaft: • = niedrig ••••• = hoch Optimum